

DRIVE AND PLAYGROUND PAINT**SPO/W449A****DESCRIPTION:**

SPO Drive and Playground Paint is a water thinned coating designed to provide colour on asphalt and tar based surfaces.

RECOMMENDED USE:

SPO Drive and Playground Paint is ideal for painting drives and playgrounds.

AVAILABILITY:

5 litre

FINISH:

Matt

COLOUR:

Red, Green, Black

TYPICAL S.G. (SPECIFIC GRAVITY):

1.25 to 1.31 @ 20 °C

VOLUME SOLIDS:

34 to 36%

WET FILM THICKNESS W.F.T

100 to 110 microns

DRY FILM THICKNESS D.F.T

35 to 40 microns

EXPECTED SPREADING RATE:

5 to 9 sq.m / litre

@ 35 microns D.F.T.

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

2.5 Poise @ 25 °C

FLASH POINT:

Non-flammable

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 1 hours @ 20 °C

Hard dry: 4 hours @ 20 °C

Full hardness: 5 to 7 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

6 hours

APPLICATION SPECIAL CONDITIONS:

N/A

VOC CONTENT:

max 41 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application Do not apply below 7 °C. restrictions

Method: Brush or Roller

Thinner Clean water
(Max vol): (10%)

Nozzle size: N/A

Nozzle N/A
pressure:

Cleaning Water
solvent:

Recoat 6 hours
interval:

SURFACE PREPARATION:

All surfaces should be clean, dry, sound and free from contaminants.

**For further advice contact SPO Technical Services at
sales@specialistpaintsonline.co.uk**

The physical constants are subject to normal manufacturing tolerances.

Existing painted surfaces should be cleaned, degreased and sanded to ensure an adequate "key" is produced. Remove all loose, flaking material and treat bare areas as new substrate then prepare accordingly.

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department at sales@specialistpaintsonline.co.uk

MIXING INSTRUCTIONS:

Mix well before use.

APPLICATION CONDITIONS:

As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying. Do not paint when temperature will be at or below 7 °C during the painting and drying process.

PRECEDING COAT:

Apply a coat of SPO Drive and Playground Paint thinned 10% with clean water on porous surfaces otherwise apply direct.

SUBSEQUENT COAT:

SPO Drive and Playground Paint.

REMARKS:

Do not paint when temperature will be at or below 7 °C during the painting and drying process.

HEALTH AND SAFETY:

See safety data sheet - SDS 11448

ISSUED:

17 August 2012

REVISION:

0

For further advice contact SPO Technical Services at
sales@specialistpaintsonline.co.uk
The physical constants are subject to normal manufacturing tolerances.

3 Kirkby Street
Hull HU2 0HE
Tel.: +44(0)1482 222421

Email: sales@specialistpaintsonline.co.uk
www.specialistpaintsonline.co.uk