

TEAK OIL**DESCRIPTION:**

SPO Teak Oil is a blend of natural oils and silicone derivatives which enhance, preserve and restore the appearance of teak and other hardwoods. It has a good degree of resistance to water and can be used inside or outside. The oil takes better to hardwood than traditional varnishes.

RECOMMENDED USE:

SPO Teak Oil is used on teak and other hardwoods, ideal for use on outdoor furniture.

AVAILABILITY:

0.5 litre, 1 litre, 2.5 litre

FINISH:

Oiled

COLOUR:

Clear

TYPICAL S.G. (SPECIFIC GRAVITY):

0.86 @ 20 °C

VOLUME SOLIDS:

34%

WET FILM THICKNESS W.F.T

N/A

DRY FILM THICKNESS D.F.T

N/A

EXPECTED SPREADING RATE:

7 sq.m / litre

Average figure dependant on the porosity of the wood.

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

Thin Liquid

FLASH POINT:

Above 32 °C (closed cup)

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 8 hours @ 20 °C

Hard dry: 24 hours @ 20 °C

Full hardness: N/A

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

16 hours or overnight

APPLICATION SPECIAL CONDITIONS:

N/A

VOC CONTENT:

Max 514 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application N/A
restrictions

Method: Brush or Cloth

Thinner N/A
(Max vol):

Nozzle size: N/A

Nozzle N/A
pressure:

Cleaning White Spirit
solvent:

Recoat 16 hours or
interval: overnight

SURFACE PREPARATION:

For further advice contact SPO Technical Services at
sales@specialistpaintsonline.co.uk

The physical constants are subject to normal manufacturing tolerances.

TEAK OIL**SPO/V601/28**

All surfaces should be clean, dry, sound and free from contaminants. Ensure the surface is left to dry for 1 to 2 weeks. Use sandpaper to remove any unwanted old coatings or paints.

MIXING INSTRUCTIONS:

Mix well before use.

APPLICATION CONDITIONS:

As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying.

PRECEDING COAT:

Apply direct to wood.

SUBSEQUENT COAT:

SPO Teak Oil

REMARKS:

Apply as a flood coat, work well into the grain, taking particular care at "end" grains.

HEALTH AND SAFETY:

See safety data sheet - SDS 11484

ISSUED:

12 March 2013

REVISION:

0

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department at sales@specialistpaintsonline.co.uk

**For further advice contact SPO Technical Services at
sales@specialistpaintsonline.co.uk**

The physical constants are subject to normal manufacturing tolerances.

3 Kirkby Street
Hull HU2 0HE
Tel.: +44(0)1482 222421

Email: sales@specialistpaintsonline.co.uk

www.specialistpaintsonline.co.uk