

WALL AND CEILING PAINT

SPO/W463/1

DESCRIPTION:

SPO Wall And Ceiling Paint is a binding wall and ceiling coating that helps prevent dust and dirt being released from the surface.

RECOMMENDED USE:

SPO Wall And Ceiling Paint can be used on plaster, render, brick, breezeblock and most timber (e.g. MDF, plywood and composites).

AVAILABILITY:

2.5 litre, 5 litre

FINISH:

Matt

COLOUR:

White

TYPICAL S.G. (SPECIFIC GRAVITY):

1.31 @ 20 °C

VOLUME SOLIDS:

32%

WET FILM THICKNESS W.F.T

75 microns

DRY FILM THICKNESS D.F.T

35 to 40 microns

EXPECTED SPREADING RATE:

13 sq.m / litre
@ 35 microns D.F.T

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

2.5 Poise @ 25 °C

FLASH POINT:

Non-flammable

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 30 mins @ 20 °C

Hard dry: 2 hours @ 20 °C

Full hardness: 5 to 7 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

6 hours @ 20 deg C

APPLICATION SPECIAL CONDITIONS:

N/A

VOC CONTENT:

Max 30 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application Do not apply below 7 °C.
restrictions

Method: Brush

Thinner Clean Water
(Max vol): (10%)

Nozzle size: N/A

Nozzle N/A
pressure:

Cleaning Water
solvent:

Recoat 6 hours @ 20
interval: deg C

SURFACE PREPARATION:

All surfaces should be clean, dry, sound and free from contaminants.

For further advice contact SPO Technical Services at
sales@specialistpaintsonline.co.uk

The physical constants are subject to normal manufacturing tolerances.

WALL AND CEILING PAINT**SPO/W463/1**

New wood should be sanded prior to coating to ensure an adequate "key" is produced.

Existing painted surfaces should be cleaned, degreased and sanded to ensure an adequate "key" is produced. Remove all loose, flaking material, then apply.

MIXING INSTRUCTIONS:

Mix well before use.

APPLICATION CONDITIONS:

Do not apply when below 7 °C. As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying.

PRECEDING COAT:

None

SUBSEQUENT COAT:

SPO Wall And Ceiling Paint

REMARKS:

Do not paint when temperature will be at 7°C or below during the painting and drying process.

HEALTH AND SAFETY:

See safety data sheet - SDS 11232

ISSUED:

26 May 2010

REVISION:

0

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department at sales@specialistpaintsonline.co.uk

**For further advice contact SPO Technical Services at
sales@specialistpaintsonline.co.uk**

The physical constants are subject to normal manufacturing tolerances.

3 Kirkby Street
Hull HU2 0HE
Tel.: +44(0)1482 222421

Email: sales@specialistpaintsonline.co.uk
www.specialistpaintsonline.co.uk