

ANTI-CLIMB PAINT**DESCRIPTION:**

SPO Anti-Climb Paint is a thick non-drying product. Coated surfaces appear normal but the paint will remain soft and slippery making the surface difficult to climb.

Intruders attempting to scale or climb a coated surface will be coated with a greasy deposit of paint.

RECOMMENDED USE:

SPO Anti-Climb Paint is for use on window ledges, down pipes, walls, gutters, anywhere which may be used as a grip point to gain unauthorised access.

AVAILABILITY:

0.8kg, 2kg

FINISH:

Semi matt

COLOUR:

Black, Red, Grey, Green

TYPICAL S.G. (SPECIFIC GRAVITY):

1.0 @ 20 °C

VOLUME SOLIDS:

84 - 90%

WET FILM THICKNESS W.F.T

0.5 mm

DRY FILM THICKNESS D.F.T

0.5 mm

EXPECTED SPREADING RATE:

1 - 2 sq.m / kilo

0.5 mm d.f.t. (based on application by brush or mitt)

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

Grease like

FLASH POINT:

above 32 °C (closed cup)

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: N/A

Hard dry: N/A

Full hardness: N/A

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

Not required

APPLICATION SPECIAL CONDITIONS:

Use at heights over 1.8 metres away from daily legitimate use.

VOC CONTENT:

144 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application N/A
restrictions

Method: Brush or mitt

Thinner Do not thin
(Max vol):

Nozzle size: N/A

Nozzle N/A
pressure:

Cleaning White spirit or
solvent: turps sub.

**For further advice contact SPO Technical Services at
sales@specialistpaintsonline.co.uk**

The physical constants are subject to normal manufacturing tolerances.

ANTI-CLIMB PAINT**SPO/C264/ -**

Recoat interval: Not required

SURFACE PREPARATION:

Ensure all surfaces are clean, dry and free from grease, oil and any other contaminants. Seal porous surfaces first. Roughen smooth surfaces using coarse abrasive paper or by wire brushing. Metal should be suitably prepared and primed prior to application.

MIXING INSTRUCTIONS:

N/A

APPLICATION CONDITIONS:

As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying.

PRECEDING COAT:

SPO Wall and Ceiling Paint on masonry and wood and other porous surfaces.

SUBSEQUENT COAT:

Not required

REMARKS:

SPO Anti-Climb Paint is for use in areas where temperatures do not normally exceed 30C. Notification signs should be used.

HEALTH AND SAFETY:

See safety data sheet - SDS 11390

ISSUED:

24 May 2012

REVISION:

0

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department at sales@specialistpaintsonline.co.uk

**For further advice contact SPO Technical Services at
sales@specialistpaintsonline.co.uk**

The physical constants are subject to normal manufacturing tolerances.

3 Kirkby Street
Hull HU2 0HE
Tel.: +44(0)1482 222421

Email: sales@specialistpaintsonline.co.uk

www.specialistpaintsonline.co.uk