

SQUASH COURT PAINT

SPO/Q1421

DESCRIPTION:

SPO Squash Court Paint is a hard wearing, high opacity, high impact resistant finish for use on squash court surrounds.

RECOMMENDED USE:

All non playing surfaces in squash courts. (Whilst it is possible to paint the playing surface, this is not recommended by the squash rackets association: If the courts are to be used for international events then these are constructed of a specialist plaster).

AVAILABILITY:

5 litre

FINISH:

Matt

COLOUR:

White

TYPICAL S.G. (SPECIFIC GRAVITY):

1.59 @ 20 °C

VOLUME SOLIDS:

WET FILM THICKNESS W.F.T

40 to 80 microns

DRY FILM THICKNESS D.F.T

23 to 35 microns

EXPECTED SPREADING RATE:

14 to 16 sq.m / litre

@ recommended D.F.T

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

4.3 to 5.5 Poise - C&P @ 25 °C

FLASH POINT:

above 32 °C (closed cup)

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 6 - 8 hours @ 20 °C

Hard dry: 16 - 24 hours @ 20 °C

Full hardness: 5 - 7 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

12 hours or overnight

APPLICATION SPECIAL CONDITIONS:

N/A

VOC CONTENT:

300 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application Do Not Spray restrictions

Method: Brush or Roller

Thinner White Spirit (5%) (Max vol):

Nozzle size: N/A

Nozzle N/A pressure:

Cleaning solvent: White Spirit

Recoat interval: 12 hours or overnight

For further advice contact SPO Technical Services at sales@specialistpaintsonline.co.uk

The physical constants are subject to normal manufacturing tolerances.

SQUASH COURT PAINT**SPO/Q1421****SURFACE PREPARATION:**

All surfaces should be clean, dry, sound and free from contaminants.

Existing painted surfaces should be cleaned, degreased and sanded to ensure an adequate "key" is produced. Remove all loose, flaking material and treat bare areas as new substrate then prepare accordingly.

MIXING INSTRUCTIONS:

Mix well before use.

APPLICATION CONDITIONS:

As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying.

PRECEDING COAT:

Apply direct to substrate.

SUBSEQUENT COAT:

SPO Squash Court Paint

REMARKS:

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department at sales@specialistpaintsonline.co.uk

HEALTH AND SAFETY:

See safety data sheet - 11419

ISSUED:

05 July 2012

REVISION:

0

**For further advice contact SPO Technical Services at
sales@specialistpaintsonline.co.uk**

The physical constants are subject to normal manufacturing tolerances.

3 Kirkby Street
Hull HU2 0HE
Tel.: +44(0)1482 222421

Email: sales@specialistpaintsonline.co.uk

www.specialistpaintsonline.co.uk