

FLUORESCENT PAINT

SPO/D125

DESCRIPTION:

SPO Fluorescent Paint is a highly visible day time coating or when used under lights at night.

RECOMMENDED USE:

SPO Fluorescent Paint is ideal on skips, bollards, bicycles, fishing floats, ships, bridges and more to identify any hazardous object. Used by sign writers, stage crews and artists. Must be used over SPO Base for Fluorescent Paint.

AVAILABILITY:

0.5 litre, 1 litre, 2.5 litre

FINISH:

Matt

COLOUR:

Orange, Red, Yellow, Green, Pink

TYPICAL S.G. (SPECIFIC GRAVITY):

1.07 @ 20 °C

VOLUME SOLIDS:

43%

WET FILM THICKNESS W.F.T

75 microns

DRY FILM THICKNESS D.F.T

30 to 35 microns

EXPECTED SPREADING RATE:

13 sq.m / litre

@ 30 microns D.F.T.

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

3.5 Poise @ 25 °C

FLASH POINT:

Above 32 °C (closed cup)

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 3 hours @ 20 °C

Hard dry: 12 hours @ 20 °C

Full hardness: 5 to 7 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

12 hours or overnight

APPLICATION SPECIAL CONDITIONS:

N/A

VOC CONTENT:

447.81 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application N/A
restrictions

Method: Brush or roller Airless Spray

Thinner White Spirit White Spirit
(Max vol): (10%) (10%)

Nozzle size: 0.013"

Nozzle 1800 to 2000 psi
pressure:

Cleaning White Spirit
solvent:

Recoat 12 hours or
interval: overnight

SURFACE PREPARATION:

All surfaces should be clean, dry, sound and free from contaminants.

**For further advice contact SPO Technical Services at
sales@specialistpaintsonline.co.uk**

The physical constants are subject to normal manufacturing tolerances.

FLUORESCENT PAINT**SPO/D125**

MIXING INSTRUCTIONS:

Mix well before use.

APPLICATION CONDITIONS:

As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying.

PRECEDING COAT:

SPO Base for Fluorescent Paint.

SUBSEQUENT COAT:

Further coats of SPO Fluorescent Paint (2 coats minimum). SPO Protective Coat for Fluorescent Paint.

REMARKS:

For best results use over SPO Base for Fluorescent Paint.

For glow in the dark paint see SPO Luminous Paint.

HEALTH AND SAFETY:

See safety data sheet - SDS 11464

ISSUED:

19 October 2012

REVISION:

0

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department at sales@specialistpaintsonline.co.uk

**For further advice contact SPO Technical Services at
sales@specialistpaintsonline.co.uk**

The physical constants are subject to normal manufacturing tolerances.

3 Kirkby Street
Hull HU2 0HE
Tel.: +44(0)1482 222421

Email: sales@specialistpaintsonline.co.uk

www.specialistpaintsonline.co.uk